

# SEAL UP®

## Hydrostop Fiber Clear

### TECHNICAL SHEET

#### DESCRIPTION

Fiber-reinforced transparent waterproofing membrane, specifically for repairing leaks, cracks, and cavities up to 5mm. Weather- and heat-resistant. Adheres effectively to all surfaces. Paintable.

#### PROPERTIES

- Quick use in all weather conditions even on rain or snow.
- It repairs quickly, usable in all weather conditions even on rain or snow.
- Suitable on dry and wet surfaces.
- It adheres to all surfaces: aluminium, zinc, lead, glass, stone, asphalt, bitumen, solid PVC, roof tiles, wood, etc.
- It can be applied to vertical surfaces.
- It fills cracks and holes of several millimeters.
- Superelastic.
- Paintable with acrylic paints.
- Fully weather resistant.
- Primer not required.
- Not resistant to solvent.
- Not suitable for EPS panels and PVC sheets.

#### APPLICATION AREAS

- To repair leaks and cracks filling.
- To seal edges around chimneys, metal Trim, gutters, concrete cracks ,etc.
- To be used as a protective product.
- To seal inside and outside of buildings: balconies, terraces, roofs, fences, etc.
- Also suitable for road pipelines.
- For motorized vehicles and boats.

#### APPLICATION

- Clean the surface and remove inconsistent parts.
- Apply a thin layer of sealant to the cracks with a brush.
- If necessary over-apply a second layer after two days.
- If pasty , to spread it more easily, dilute it to 10% with nitro solvent or a hydrocarbon-based detergent.

#### CONSERVATION

Store in the original packing in a cool place and protected from direct sunlight, at a temperature between 5°C and 25°C.

After this period, it does not necessarily mean that the sealant is unusable. The properties should be checked before application to ensure suitability for the intended use.

#### TECHNICAL PROPERTIES

##### Uncured sealant

Base	Synthetic resin with fiber-reinforced solvents
Appearance	Transparent paste
Curing mechanism	Solvent evaporation
Curing time	24-48 h
Specific weight	1050 ± 10 kg/m <sup>3</sup>
Application temperature	from -10°C to 40°C

##### Cured sealant

Elongation at break (%)	20 - 30
Temperature resistance	from -25°C to +100°C
Consumption	1 L / m <sup>2</sup>

#### PACKAGING

Code	931
Format	1 L dose
Box	6 pieces
Pallet	110 boxes
Shelf life	36 months